



Eden Research Laboratory

To: BioSphere

Date: March 22, 2016

From: Thomas Poth

Number of pages including cover: 1

Regarding: ASTM D 5511-11 test update for White Bags LDPE- 856 days

# Update

2111 Menaul NE, Suite A  
 Albuquerque, NM 87107  
 T 505.508.3994  
 M 505.550.9316  
 thomas.poth@edenresearchlab.com

	Inculum	Negative	Positive	865 - White Bags LDPE
Cumulative Gas Volume (mL)	2375.4	2289.0	11198.1	14608.4
Percent CH <sub>4</sub> (%)	44.2	41.6	41.8	53.9
Volume CH <sub>4</sub> (mL)	1049.1	951.4	4678.3	7877.8
Mass CH <sub>4</sub> (g)	0.75	0.68	3.34	5.63
Percent CO <sub>2</sub> (%)	40.3	38.8	41.9	35.5
Volume CO <sub>2</sub> (mL)	957.7	887.9	4690.2	5186.1
Mass CO <sub>2</sub> (g)	1.88	1.74	9.21	10.19
Sample Mass (g)	1,000	10	10	8.0
Theoretical Sample Mass (g)	0.0	8.6	4.4	6.9
Biodegraded Mass (g)	1.08	0.99	5.02	7.00
Percent Biodegraded (%)		-1.0	89.2	86.4

## Biodegradation

